

ARAMID ELYAF KUMAŞLAR

URUN KODU	threadxcm		elyaf		kalınlık	ağırlık			dokuma	
	çözgü	atkı	çözgü	atkı		çözgü	atkı	toplam		
	UNI EN 1049-2		TEX		(mm)+-15%	(gr/m2)+-4%			UNI 8099	
					UNI EN ISO 5084	UNI 5114-82				
KEVLAR®49-DuPont										
STYLE	120	13	13	215	215	0,08	30	30	60	plain
STYLE	220	9,5	9,5	420	420	0,12	40	40	80	plain
STYLE	115	13,3	13,3	420	420	0,15	58	58	115	plain
STYLE	181	20	20	420	420	0,23	84	84	168	8 H satin
STYLE	281	6,7	6,7	1270	1270	0,25	86,5	86,5	173	plain
STYLE	285	6,7	6,7	1270	1270	0,25	86,5	86,5	173	crowsfoot satin
STYLE	282	6,7	6,7	1270	1270	0,25	86,5	86,5	173	twil 2/2
STYLE	143	39	8	420	220	0,30	163	163	196	crowsfoot satin
STYLE	243	15	7	1270	420	0,30	190	30	220	crowsfoot satin
STYLE	328	6,7	6,7	1580	1580	0,33	111	111	223	plain
STYLE	335	6,7	6,7	1580	1580	0,33	111	111	223	crowsfoot satin
STYLE	279	4,4	4,3	3160	3160	0,32	139	136	275	twil 2/2
STYLE	900	6,7	6,7	2400	2400	0,40	163	163	326	5 H satin
STYLE	1050	11	11	1580	1580	0,46	178	178	356	basket 4/4
STYLE	380	15,5	2	2400	215	0,40	375	5	380	oxford 2/1
STYLE	1350	9,3	9,3	2400	2400	0,68	225	225	450	basket 4/4
STYLE	1033	7,85	7,85	3160	3160	0,62	260	225	520	basket 4/4

